

LMM14 Laser Settings



Laser Settings for LMM14 Materials



USA Tel: (336) 288-1613 Toll Free (866) 288-1613
 sales@jorlink.com or support@jorlink.com

The following table details recommended laser settings for LMM14 materials on a range of common substrates. These settings are designed to help guide the user to the optimum parameters as quickly as possible. Please note that there will be variations in substrate finish and between different brands of laser. It may still be necessary to perform further refinement of settings to achieve the desired mark.

LMM14 Suggested Laser Settings Used for CO ₂ X-Y Laser						
Substrate Material	Settings 45W laser		Settings 30W laser		Lens	DPI/PPI
	Power (W)	Speed (in/sec)	Power (W)	Speed (in/sec)		
Stainless Steel	41	98	30	77	2"	1000/1000
Stainless Steel - Bright Annealed	30	63	30	63	2"	1000/1000
Galvanized Steel	41	98	30	49	2"	1000/1000
Brass	45	35	30	28	2.5"	1000/1000
Aluminum	45	35	30	21	2"	1000/1000
Copper	45	28	30	10	2"	1000/1000
Chrome plating	30	28	30	28	2.5"	1000/1000
Nickel Plating	41	42	30	31	2"	1000/1000
Gold Plating	45	21	30	14	2"	1000/1000
Silver Plating	45	11	30	7	2"	1000/1000
Titanium	29	126	29	126	1.5"	1000/1000
Pewter	41	70	30	50	2"	1000/1000

LMM14 Laser Settings



Suggested Laser Settings Used for Beam Steered ND:YAG or Fiber Laser with a 100mm lens

Material	Power (W)	Speed (cm/sec)	Hatch Spacing “	CW Mode or Q-Switch Freq
Stainless Steel	8	25	.002	CW / ≥ 50 KHz
Stainless Steel - Bright Annealed	7	25	.002	CW / ≥ 50 KHz
Galvanized Steel	7	15	.002	CW / ≥ 50 KHz
Brass	10	15	.002	CW / ≥ 50 KHz
Aluminum	10	10	.002	CW / ≥ 50 KHz
Chrome plating	10	12	.002	CW / ≥ 50 KHz
Nickel Plating	10	30	.002	CW / ≥ 50 KHz
Gold Plating	10	15	.002	CW / ≥ 50 KHz
Silver Plating	10	3	.002	CW / ≥ 50 KHz
Titanium	5	30	.002	CW / ≥ 50 KHz
Pewter	10	50	.002	CW / ≥ 50 KHz



USA Tel: (336) 288-1613 Toll Free (866) 288-1613
sales@jorlink.com or support@jorlink.com